

# NSW Sand Specifications

SAND SOURCE - Raymond Terrace

SAND TYPE - Washed sand

<b>Aperture size</b>	<b>Test method</b>	<b>Specification limits</b>
4.75 mm	AS 1141.11	100%
2.36 mm	AS 1141.11	100%
1.18 mm	AS 1141.11	98 - 100%
600 um	AS 1141.11	90 - 100%
300 um	AS 1141.11	20 - 44%
150 um	AS 1141.11	0 - 6%
75 um	AS 1141.11	0 - 2%
<b>Properties</b>	<b>Test method</b>	<b>Specification limits</b>
Fineness modulus		1.3 - 1.8
Moisture content	AS 1289.2.1	0 - 10%
Clay/Silt content	AS 1141.33	0 - 8%